



**ProWise  
PVA Primer  
125 Line**

Type	Sheen	Spread Rate	Recommended Application	Thinner	Clean Up	DRY TIME		
						Tack Free	Re-coat	Cure
Latex	Flat	Up to 400 Sq Ft Per Gallon	Brush, Roller or Spray	Clean Water	Warm Soapy Water	1 Hour	2 Hours	7 Days
<b>PRODUCT NAME:</b> 125 Line ProWise PVA Primer		A high quality professional interior latex primer and sealer for use on unpainted drywall, skim coated drywall, gypsum, cured plaster and masonry, and previously painted surfaces. Formulated for easy application, ProWise PVA Primer dries quickly, gives good coverage, seals surface to eliminate flashing to top coat. Quick dry may be sanded or recoated in two hours.						
<b>WHERE TO USE:</b>		Drywall                      On interior wall surfaces prior to topcoating. Will provide an even Masonry                      seal and hold-lout for subsequent finish coats.						
<b>SURFACE PREPARATION:</b>		Stir thoroughly before using. Surface must be clean, dry and free of dirt, grease and grime. Remove all loose and flaking paint. Fill all holes cracks, and surface defects. Sand to a smooth finish. Remove rust and prime all unpainted metal with O'Leary Metal Primer, or O'Leary Industrial Primer. Dull glossy surfaces by sanding. Prime new wood with O'Leary Enamel Undercoat. Fill cinder block and rough masonry with O'Leary Acrylic Block Filler. For best coverage primers and block fillers should be tinted to approximate finish color. Concrete and plaster must cure at least 30 days before painting. Ph must be 10.0 or lower. For Ph greater than 10.0 use #50 Block It (up to Ph12) or 5090 Primer/Sealer (up to Ph 13).						
<b>APPLICATION:</b>		Stir product with a circular, lifting motion before you begin to paint. May be applied by brush, roller or spray, at a rate of application not to exceed 400 square feet per gallon. Surface texture and porosity will affect actual yield. For best brush results, use a quality synthetic filament brush. For roller application, use a 3/8" nap cover for smooth surfaces, a 1/2" nap cover for semi-rough surfaces and a 3/4" nap cover for rough surfaces. For spray application, may be thinned with clean water, up to 10% reduction if necessary. Satisfactory results are most likely obtained by using quality application tools. Apply when surface temperature is above 50° F.						
<b>NOTE: Formulated without mercury or lead.</b>								

<b>RESIN TYPE:</b>	Vinyl Acetate / Acrylic
<b>SOLIDS:</b>	Weight – 43.4% Volume – 30.7%
<b>WEIGHT PER GALLON:</b>	10.4 lbs.
<b>VISCOSITY:</b>	104 – 109 (Krebs Units)
<b>SPECULAR GLOSS:</b>	1 – 2% @ 85 degrees
<b>RECOMMENDED FILM THICKNESS:</b>	Wet – 3.5 to 4.0 mils Dry – 1.1 to 1.2 mils
<b>VOC – VOS STATEMENT:</b>	This product contains less than 0.42 lbs or 50 GPL per gallon.
<b>CAUTIONS:</b>	<b>CAUTION!</b> Do not take internally. Close container after each use. <b>KEEP OUT OF REACH OF CHILDREN.</b> <b>KEEP FROM FREEZING.</b>

09/22/15

