



**Pro Prime
Wood Primer / Sealer
Interior Alkyd
37 - 11**

SECTION NO. 3 ADS-402

Type	Sheen	Spread Rate	Recommended Application	Thinner	Clean Up	DRY TIME		
						Tack Free	Re-coat	Cure
Alkyd	Flat	Up to 350 Sq Ft Per Gallon	Brush, Roller, or Spray	Mineral Spirits	Mineral Spirits	2 – 3 Hours	Overnight	7 Days
PRODUCT NAME: 37 - 11 PRO PRIME WOOD PRIMER/SEALER INTERIOR ALKYD		Pro Prime Wood Primer/Sealer is designed for the professional applicator or homeowner for use as a universal undercoat-primer for woodwork or walls. It may be top-coated with alkyd or latex enamel finishes.						
WHERE TO USE:		<p>WOOD: Sand smooth and apply one coat of Alkyd Wood Primer/Sealer. Allow to dry overnight, sand lightly and apply one or two coats of Alkyd or Latex Semi-Gloss Enamel.</p> <p>PLASTER AND DRYWALL: Apply one coat of Latex primer Sealer, followed by a coat of this primer undercoat allowing at least 4 hours to dry between coats. Finish with one or two coats of Alkyd or Latex Semi-Gloss or High Gloss Enamel.</p> <p>METAL: Clean rust free metal may be primed with one coat of Alkyd Wood Primer/Sealer. Allow 24 hours before recoating with one or two coats of Alkyd or Latex Semi-Gloss or High Gloss Enamel.</p> <p>EXTERIOR WOOD: Apply one coat of Alkyd Wood Primer/Sealer allowing to dry overnight prior to topcoating with Latex or Alkyd Enamel. This system is not intended for use as a house paint. It is intended for use on trim areas such as doors, window frames, fascia boards and porch or step railings.</p>						
SURFACE PREPARATION:		Surface to be painted must be clean and free of dirt, chalk, wax, grease, rust or loose, flaking paint. Dirt and chalk should be removed by scrubbing with warm soapy water and thoroughly rinsed with clean water. Wax should be removed with a commercial wax stripper or by solvent cleaning. Grease should be cleaned by using Coronado Sur-Prep I. Rust must be removed by hand sanding vigorously or by conscientious power tool cleaning. Remove loose paint by scraping. Feather sand rough edges to insure a smooth finish coat. Glossy surfaces must be dulled by lightly sanding. Remove sanding dust before paint application.						
APPLICATION:		Stir product with a circular, lifting motion before you begin to paint. Pro Prime Wood Primer/Sealer may be applied by brush, roller, or spray techniques, at a rate of application not to exceed 350 sq ft per gallon. Surface texture and porosity will affect actual yield. For best brush application results, use a quality natural bristle brush. For roller application use a ¼" nap cover for smooth surfaces, 3/8" or 1/2" nap cover for semi-rough surfaces and a ¾": nap cover for rough surfaces. Thinning is not normally necessary, if required use mineral spirits sparingly.						
NOTE: Formulated without mercury or lead.								

RESIN:	Soya Tall Alkyd												
SOLIDS:	Weight – 70.3% Volume – 48.6%												
WEIGHT PER GALLON:	12.44 lbs.												
VISCOSITY:	80 – 85 (Krebs Units)												
FLASH POINT:	100° F (TT-P-141, Method 4293)												
SPECULAR GLOSS:	0 – 3% @ 85 Degrees												
SAG RATING:	Pass 8 mills (Lenetta)												
RECOMMENDED FILM THICKNESS:	Wet – 4.0 – 4.5 MILS Dry – 2.0 – 2.2 MILS												
LIGHT REFLECTANCE:	N / A												
VOC – VOS STATEMENT:	This product contains less than 2.9 lbs or 350 GPL per gallon.												
CAUTIONS:	<p style="text-align: center;">CAUTION! Combustible Contains Mineral Spirits</p> <p>Keep away from heat & flame. To avoid breathing vapors or spray mist, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headaches or dizziness, increase fresh air or wear respiratory protection (NIOSH/MSHA TC23C or equivalent) or leave the area. Close container after each use. Avoid contact with skin. Use with adequate ventilation. NOTICE: Reports have associated repeated and prolonged occupational overexposure to solvents with permanent brain & nervous system damage. Intentional misuse by deliberately concentrating and inhaling the contents may be harmful or fatal.</p> <p style="text-align: center;">KEEP OUT OF REACH OF CHILDREN.</p>												
Chemical Abstract Number:	<table> <thead> <tr> <th>Ingredient:</th> <th>CAS NO.</th> </tr> </thead> <tbody> <tr> <td>Titanium Dioxide</td> <td>13463-67-7</td> </tr> <tr> <td>Alkyd Resin</td> <td>Proprietary</td> </tr> <tr> <td>Calcium Carbonate</td> <td>1317-65-3</td> </tr> <tr> <td>Aluminum Silicate</td> <td>1318-74-7</td> </tr> <tr> <td>Mineral Spirits</td> <td>8052-41-3</td> </tr> </tbody> </table>	Ingredient:	CAS NO.	Titanium Dioxide	13463-67-7	Alkyd Resin	Proprietary	Calcium Carbonate	1317-65-3	Aluminum Silicate	1318-74-7	Mineral Spirits	8052-41-3
Ingredient:	CAS NO.												
Titanium Dioxide	13463-67-7												
Alkyd Resin	Proprietary												
Calcium Carbonate	1317-65-3												
Aluminum Silicate	1318-74-7												
Mineral Spirits	8052-41-3												
Federal Specifications:	Meets the performance requirements of: TT-E-543 and TTE - 545.												