



ACRYMAX
Solid Color Acrylic
Latex Stain
5360

Type	Sheen	Spread Rate	Recommended Application	Thinner	Clean Up	DRY TIME		
						Tack Free	Re-coat	Cure
Acrylic Blend	Flat	125 - 300 Sq Ft Per Gallon	Brush, Roller or Spray	Clean Water	Warm Soapy Water	30 Minutes	4 Hours	7 Days
PRODUCT NAME: 5360 Acrymax Solid Color Acrylic Latex Stain		Acrymax Solid Color Stain has excellent adhesion, flexibility, open-time and superior weather resistance. The acrylic finish resists cracking, peeling, staining and the growth of mildew on the coating film. Acrymax Solid Color Stain performs well on vertical wood and masonry surfaces. The product is self-priming on masonry and non-bleeding wood; Pro Prime Acrylic Wood Primer or Pro Prime Bonding Primer are recommend on bleeding woods.						
WHERE TO USE:		On exterior vertical surfaces, such as wood siding, shakes, fences, or beams.						
Surface Preparation:		<p>Surface to be painted must be clean and free of dirt, chalk, rust and loose or flaking paint. Dirt and chalk should be removed by power washing or hand scrubbing with cleanser and water, followed by a clean water rinse. Rust must be removed by sanding or by conscientious power tool cleaning. Remove loose paint by scraping. Feather sand rough edges to insure a smooth finish coat. Glossy surfaces must be dulled by lightly sanding. Remove sanding dust before paint application. Any exposed substrate should be spot primed with the appropriate primer.</p> <p>Priming – (New or Bare Surfaces) WOOD – Use Pro-Prime 4790 Acrylic Wood Primer or 2090 Acrylic Bonding Primer MASONRY – Use O’Leary, 5090 Pro Primer Barrier Coat. To fill porous block, use O’Leary 529-11 Pro Prime Block Filler FERROUS METAL – Rust Inhibiting Metal Primer NON-FERROUS METAL – Use O’Leary 50 Block It</p> <p>WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.</p>						
Application:		Stir the product thoroughly prior to use and periodically during application. Solid Color Acrylic Stain may be applied by brush, roller or spray. To ensure uniform color and wood grain prominence, flow stain on with a full applicator following the grain pattern. Always maintain a wet edge to paint into. Spray should be followed by brushing into surface, especially on weathered surfaces. The spread rate of Acrymax Solid Color Acrylic Stain is 125 to 300 sq ft per gallon depending on surface texture and porosity. No thinning is recommended for this product. Avoid painting over hot surfaces or in direct sunlight. Can be applied if surface and air temperatures are above 50°F. Do not apply if rain is threatening.						
NOTE: Formulated without mercury or lead.								

Resin Type:	Acrylic Blend
Solids:	Volume – 32%
Weight Per Gallon:	10.58 lbs.
Viscosity:	83 – 87 (Krebs Units)
Specular Gloss:	1 – 2% @ 85 Degrees
Recommended Film Thickness:	Wet - 5.35 to 12.8 mils Dry - 1.69 to 4.0 mils
VOC – VOS Statement:	This product contains less than 0.84 lbs or 100 GPL per gallon.
Cautions:	CAUTION ! Do not take internally. Close container after each use. KEEP OUT OF REACH OF CHILDREN !

Rev. 02/1/2023

