



Pro Prime Hi-Hiding
DRYWALL PRIMER / SEALER
1190
 SECTION NO. 3 ADS-404

Type	Sheen	Spread Rate	Recommended Application	Thinner	Clean Up	DRY TIME		
						Tack Free	Re-coat	Cure
Vinyl Acetate/ Acrylic	Flat	Up to 400 Sq Ft Per Gallon	Brush, Roller, Pad or Spray	Clean Water	Warm Soapy Water	60 Minutes	2 Hours	7 Days
PRODUCT NAME: 1190 Pro Prime Hi-Hiding Drywall Primer / Sealer		Recommended for interior use on new drywall, plaster, spackled areas, masonry and block surfaces. Formulated for easy application. Latex/Primer Sealer dries quickly, gives good coverage, and seals substrate to eliminate flashing of top coat.						
WHERE TO USE:		Plaster Drywall	On interior wall surfaces prior to top-coating. Will provide an even seal and excellent hold-out for subsequent finish coats.					
SURFACE PREPARATION:		Surface must be clean and free of dirt, grease and grime. Remove all loose and flaking paint. Fill all holes, cracks and surface defects. Sand to smooth finish. Remove rust and prime all unpainted metal with 560 O'Leary Metal Primer, or O'Leary Industrial Primer. Dull glossy surfaces by sanding. Prime new wood with O'Leary 37-11 Enamel Undercoat. Fill cinder block and rough masonry with O'Leary Vinyl Block Filler. For best coverage primers and block fillers should be tinted to approximate finish color.						
APPLICATION:		Stir product with a circular, lifting motion before you begin to paint. Latex Primer/Sealer may be applied by brush, roller, pad or spray, at a rate of application not to exceed 400 square feet per gallon. Surface texture and porosity will effect actual yield. For best brush results, use a quality synthetic filament brush. For roller application, use a 3/8" nap cover for smooth surfaces, a 1/2" nap cover for semi-rough surfaces and a 3/4" nap cover for rough surfaces. For spray application, Latex Primer/Sealer may be thinned with clean water, up to 10% reduction if necessary. Satisfactory results are most likely obtained by using quality application tools. Apply when surface temperature is above 50° F.						
NOTE: Formulated without mercury or lead.								

RESIN:	Vinyl Acetate / Acrylic
SOLIDS:	Weight – 45.1% Volume – 29.5%
WEIGHT PER GALLON:	10.60 lbs.
VISCOSITY:	96 – 98 (Krebs Units)
SPECULAR GLOSS:	3 – 5% @ 85 Degrees
RECOMMENDED FILM THICKNESS:	Wet – 3.5 to 4.0 Mils Dry – 1.07 to 1.2 Mils
VOC – VOS STATEMENT:	This product contains less than .83 lbs or 100 GPL per gallon.
CAUTIONS:	<p>CAUTION!</p> <p>Do not take internally. Close container after each use.</p> <p>KEEP OUT OF REACH OF CHILDREN.</p> <p>KEEP FROM FREEZING.</p>

