



Wash – N – Wear

Latex / Satin Finish

1300 LINE

SECTION NO. 2 ADS 301

| Type | Sheen | Spread Rate | Recommended Application | Thinner | Clean Up | DRY TIME | | |
|--|-------------|--|-----------------------------|-------------|------------------|------------|---------|---------|
| | | | | | | Tack Free | Re-coat | Cure |
| 100% Acrylic | Satin Gloss | Up to 400 Sq Ft Per Gallon | Brush, Roller, Pad or Spray | Clean Water | Warm Soapy Water | 60 Minutes | 4 Hours | 30 Days |
| PRODUCT NAME: 1300 LINE Wash - N- Wear Latex / Satin Finish | | This Acrylic Satin Enamel is particularly suited for interior surface areas requiring routine washing. Bathrooms, kitchens, family rooms, laundry rooms, children's bedrooms, are ideal places for this coating. Spatter resistance and good leveling properties makes this latex enamel finish an excellent choice for do-it-yourselfers or professional painters. | | | | | | |
| WHERE TO USE: | | Drywall Plaster Wood Metal Masonry On interior surfaces where easy stain removal is a requirement. The subtle sheen of this product provides a very durable, scrubbable finish. | | | | | | |
| Surface Preparation: | | Surface to be painted must be clean and free of dirt, chalk, wax, grease, rust, or loose, flaking paint. Dirt and chalk should be removed by scrubbing with warm soapy water and thoroughly rinsed with clean water. Wax should be removed with a commercial wax stripper or by solvent cleaning. Grease should be cleaned by using Coronado Sur-Prep 1. Rust must be removed by hand sanding or by conscientious power tool cleaning. Remove loose paint by scraping. Feather sand rough edges to insure a smooth finish coat. Glossy surfaces must be dulled by lightly sanding. Remove sanding dust before paint application. Any exposed substrate should be spot primed with the appropriate primer. Priming - (new or bare surfaces) Drywall – Self- Priming, but for best results use #4190 Latex Primer Sealer. Plaster – For best results, use #50 BlockOut, #2000 Sungard. Wood – Alkyd Primer Undercoat, #37-11. Ferrous Metal – Rust inhibiting metal primer such as #35-111, #2090, or #925-147. Non-Ferrous Metal – PermaBond #100-10. Galvanized - #100-10 or #36-11. Masonry – Masonry Sealer #43-10, #48-11, Block Filler #946-11. | | | | | | |
| Application: | | Stir product with a circular, lifting motion before you begin to paint. Acrylic Satin Enamel may be applied by brush, roller, pad, or spray techniques, at a rate of application not to exceed 400 sq ft per gallon. Surface texture and porosity will effect actual yield. For best brush application results, use a quality synthetic bristle brush. For roller application, use a 3/8" nap cover for smooth surfaces, a 1/2" or 3/4" nap cover for semi-rough surfaces and a 1" nap cover for rough surfaces. For spray application, Acrylic Satin Enamel may be thinned with clean water, up to 10% reduction if necessary. This product will dry to the touch in 60 minutes. May be re-coated in 4 hours. Allow a minimum of 10 days cure time before washing. Clean up is simply accomplished with warm soapy water before paint dries. When dry, this paint is difficult to remove, keep a wet rag handy to clean up any spills immediately. Thinning is not normally necessary. If required, use clean water sparingly. Apply when surface temperature is above 50°F. Examine the contents for proper color as we cannot be responsible for incorrect color after application. | | | | | | |
| NOTE: Formulated without mercury or lead. | | | | | | | | |

| | |
|------------------------------------|---|
| Resin: | Acrylic / Vinyl Acrylic |
| Solids: | Weight – 51.7% Volume – 38.3% |
| Weight Per Gallon: | 10.62 lbs. |
| Viscosity: | 90 – 94 (Krebs Units) |
| Specular Gloss: | 45 – 55% @ 85 Degrees |
| Recommended Film Thickness: | Wet – 3.5 to 4.5 mils Dry – 1.3 to 1.7 mils |
| VOC – VOS Statement: | This product contains less than 3.17 lbs. or 250 G.P.L. per gallon. |
| Cautions: | CAUTION! Do not take internally. Close container after each use. KEEP OUT OF REACH OF CHILDREN. |