



**ProWise  
FLAT FINISH  
120 LINE**

Type	Sheen	Spread Rate	Recommended Application	Thinner	Clean Up	DRY TIME		
						Tack Free	Re-coat	Cure
Vinyl Acrylic	Flat	300 to 400 Sq Ft Per Gallon	Brush, Roller, Pad or Spray	Clean Water	Warm Soapy Water	60 Minutes	4 Hours	30 Days
<b>PRODUCT NAME:</b> 120 Line ProWise Flat		ProWise Flat is a dead flat interior wall and ceiling finish, formulated to for excellent coverage and touch-up. This high build dead flat latex finish helps to hide minor drywall imperfections with its' high build, dead flat film.						
<b>WHERE TO USE:</b>		Drywall Plaster Wood Masonry This flat latex wall paint is a very low odor, low VOC product, making it perfect for homes, hospitals, schools, or any area where odor is a concern.						
<b>Surface Preparation:</b>		<b>New Work:</b> The surface to be coated must be clean and free of oil, grease, rust and other contaminants that could interfere with adhesion. Masonry surfaces should be fully cured. <b>Priming –</b> Drywall / Plaster – Prime with 125 ProWise Primer or this product. Wood – Prime with 125 ProWise Primer. Ferrous Metal – Prime bare metal –w- a rust inhibiting metal primer. Non-Ferrous Metal – Dull new non-ferrous metal with a maroon scrub pad and Prime with 145 CeramicWise Primer. Masonry – Prime with poured or precast masonry with 135 TechWise Primer. Fill porous block 136 TechWise Acrylic Block Filler or 126 ProWise Latex Block Filler. <b>Repaint Work:</b> Remove any oil, chalk, dirt, wax or dust prior to re-coating. Any loose or flaking paint should be removed, patched and the edges feather sanded to produce a smooth, uniform surface. Dull glossy surfaces to insure good adhesion. On previously painted surfaces in good repair, no priming is generally necessary. Spot prime bare areas with this product or the primer indicated above.						
<b>Application:</b>		Stir product with a circular, lifting motion before you begin to paint. Pro-Tech Satin Enamel may be applied by brush, roller, pad or spray techniques, at a rate of application not to exceed 400 sq ft per gallon. Surface texture and porosity will effect actual yield. For best brush application results, use a quality synthetic filament brush. For roller application, use a 3/8" nap cover for smooth surfaces, a 1/2" nap cover for semi-rough surfaces. Do not jeopardize the success of your painting project by using poor quality applicator tools. Apply only when surface and air temperatures are between 50°F and 90°F. <b>Airless</b> – Tip size at atomization pressures will vary with type of equipment, viscosity and temperature. An orifice of .013 - .017 will provide the most satisfactory spray pattern.						
<b>NOTE: Formulated without mercury or lead.</b>								

<b>Resin:</b>	Vinyl Acrylic
<b>Solids:</b>	Volume – 37.2%
<b>Weight Per Gallon:</b>	11.91 lbs.
<b>Viscosity:</b>	110 – 113 (Krebs Units)
<b>Specular Gloss:</b>	1 – 2 @ 85 degrees
<b>Recommended Film Thickness:</b>	Wet – 4.0 to 5.35 mils Dry – 1.5 to 2.0 mils
<b>VOC – VOS Statement:</b>	This product contains less than 0.42 lbs. or 50 GPL per gallon of coating.
<b>Cautions:</b>	<p><b>CAUTION!</b> Do not take internally. Close container after each use.</p> <p><b>KEEP OUT OF REACH OF CHILDREN.</b></p>

03/15/18

