



**PRO-TECH FLAT**  
**100% Acrylic**  
**Exterior Latex**  
**5350 Line**  
*Formerly 4700 Line*

| Type  | Sheen | Spread Rate   | Recommended Application     | Thinner     | Clean Up         | DRY TIME   |         |            |
|---|-------|---|-----------------------------|-------------|------------------|------------|---------|------------|
|   |       |   |                             |             |                  | Tack Free  | Re-coat | Cure       |
| 100% Acrylic Latex  | Flat  | Up to 400 Sq Ft Per Gallon  | Brush, Roller, Pad or Spray | Clean Water | Warm Soapy Water | 60 Minutes | 4 Hours | 10-14 Days |
| <b>PRODUCT NAME:</b><br>5350 LINE<br>Pro-Tech<br>100% Acrylic<br>Exterior Latex<br>Flat |       | This Latex House Paint is designed for service over new or previously painted surfaces in good condition. It is formulated to cover all surfaces in one coat when applied at the rate of 400 sq ft per gallon. Latex House Paint dries dust and bug free in one hour. Provides a durable and protective finish on any properly primed and prepared exterior surface. Recommended for use on aluminum, vinyl, and wood siding, clapboard, shakes, shingles, plywood, masonry and primed metal down to a surface and air temperature of 35° F.  |                             |             |                  |            |         |            |
| <b>WHERE TO USE:</b>  |       | Wood                      On exterior siding, foundations, fascia, shutters or retaining walls.<br>Hardboard<br>Masonry<br>Metal<br>Galvanized  |                             |             |                  |            |         |            |
| <b>Surface Preparation:</b>   |       | When air temperature is at 35° F, substrates may be colder; prior to painting, check to be sure the air, surface, and material temperature are above 35° F. and at least 5° F above the dew point. Avoid using if rain or snow is expected.<br><br>Surface to be painted must be clean and free of dirt, chalk, wax, grease, rust or loose, flaking paint. Dirt and chalk should be removed by power washing, or hand scrubbing, with an abrasive cleanser and water, followed by a clean water rinse. Wax should be removed by solvent cleaning. Grease and oil should be cleaned by using Coronado Sur-Prep 1. Rust must be removed by blasting, hand sanding vigorously or by conscientious power tool cleaning. Remove loose paint by scraping. Feather sand rough edges to insure a smooth finish coat. Glossy surfaces must be dulled by lightly sanding. Remove sanding dust before paint application. Any exposed substrate should be spot primed with the appropriate primer.<br><b>Priming – (new or bare surfaces)</b><br>WOOD – Use O'Leary Exterior Acrylic Primer #2090 or #560 Oil Primer<br>MASONRY – Use Primer Sealer #43-10 or #48-11. To fill porous block, use #946-11 Latex Block Filler.<br>FERROUS METAL – Rust Inhibiting Metal Primer such as #35-111, #2090 or #925-147.<br>GALVANIZED – Use Acrylic Primer #36-11 or #180-11. |                             |             |                  |            |         |            |
| <b>Application:</b>   |       | Stir product with a circular, lifting motion before you begin to paint. May be applied by brush, spray, pad or roller, at a rate of up to 400 sq ft per gallon. Surface texture and porosity will effect actual yield. For best brush application results, use a quality synthetic filament brush. For the roller application, 3/8" nap cover. For spray application, thin with clean water, up to 10% reduction if necessary. Do not apply to hot surfaces or in direct sunlight. Do not apply if rain is threatening.   |                             |             |                  |            |         |            |
| <b>NOTE: Formulated without mercury or lead.</b>  |       |   |                             |             |                  |            |         |            |

|                                    |   |
|------------------------------------|---|
| <b>Resin Type:</b>                 | 100 % Acrylic   |
| <b>Solids:</b>                     | Weight – 46%<br>Volume – 34%  |
| <b>Weight Per Gallon:</b>          | 10.5 lbs.   |
| <b>Viscosity:</b>                  | 91 – 96 (Krebs Units)   |
| <b>Specular Gloss:</b>             | 2 – 4% @ 85 Degrees   |
| <b>Recommended Film Thickness:</b> | Wet – 3.5 to 4.0 mils<br>Dry – 1.3 to 1.5 mils  |
| <b>VOC – VOS Statement:</b>        | This product contains less than 0.83 lbs. or 100 GPL per gallon.  |
| <b>Cautions:</b>                   | <b>CAUTIONS!</b><br><b>Do not take internally. Close container after each use.</b><br><br><b>KEEP OUT OF REACH OF CHILDREN.</b> |

Rev. 02/16/2021

