



SUPER KOTE ACRYLIC TRAFFIC PAINT

66 LINE

SECTION NO. 12 ADS-1302

Type	Sheen	Spread Rate	Recommended Application	Thinner	Clean Up	DRY TIME		
						Tack Free	Re-coat	Cure
Vinyl Acetate Acrylic	Flat	3" line / 400' 4" line / 300' 5" line / 240' 6" line / 200'	Brush, Roller, Pad or Spray	Clean Water	Warm Soapy Water	30 Minutes	4 Hours	7 Days
Product Name: 66 LINE Super Kote Acrylic Traffic Paint		A fast drying paint for marking traffic lanes on streets, highways, parking lots, warehouses and other areas where such marking is required. Traffic beads may be dropped into this coating while wet to provide reflectorized markings. If beads are applied, they should be broadcast into the wet paint at a rate of 6 lbs. of beads per gallon of paint.						
WHERE TO USE:		Concrete Asphalt	On interior or exterior horizontal surfaces such as streets, highways, parking lots or warehouses.					
Surface Preparation:		Surface to be marked must be clean, free of dust, oil, grease, wax, rust or bleeding stains. Any asphaltic seal coat applied to the surface prior to application of this traffic paint should be dry for at least 48 hours before this traffic paint is used.						
Application:		May be applied by brush, roller, spray, hand or automatic line markers. Do not apply when air or surface temperatures are below 50°F. Do not apply to extremely hot surfaces. Stir contents thoroughly from the bottom before using. Paint only in dry weather. Thinning is not normally required, if necessary, thin sparingly with clean water. This Acrylic Traffic Paint will dry to no pickup (ASTM D-711) in 30 minutes at 70° to 80°F. Super Kote Acrylic Traffic Paint is not designed as an anti-slip coating. If skid resistance is important, apply Coronado Step-Safer.						
NOTE: Formulated without mercury or lead.								

Resin Type:	Vinyl Acetate / Acrylic		
Solids:	Weight	6601 68.9%	6656 64.89%
	Volume	50.5%	47.0%
Weight Per Gallon:		6601 13.02 lbs	6656 12.11 lbs
Viscosity:	80 – 85 (Krebs Units)		
Flash Point:	200°F. (TT-P-141, Method 4293)		
Specular Gloss:	2 – 3% @ 85 degrees		
Sag Rating:	N/A		
Recommended Film Thickness:	Wet - 12.0 to 15.0 mils Dry - 3.4 to 4.2 mils		
Light Reflectance:	90% (White)		
Cautions:	CAUTION! Do not take internally. Close container after each use. KEEP OUT OF REACH OF CHILDREN KEEP FROM FREEZING		
VOC / VOS Statement:	This product contains a maximum of 0.6 lbs VOC/VOS per gallon of coating.		
Chemical Abstract Number:	Ingredient:	6601	CAS. NO.
	Titanium Dioxide		13463-67-7
	Calcium Carbonate		1317-65-3
	Acrylic Resin		Proprietary
	Water		7732-18-5