



**Wash-N-Wear**  
**Latex/Eggshell Finish**  
**1000 Line**  
 SECTION NO. 2 ADS-320

Type	Sheen	Spread Rate	Recommended Application	Thinner	Clean Up	DRY TIME		
						Tack Free	Re-coat	Cure
Acrylic	Eggshell	Up to 350 Sq Ft Per Gallon	Brush, Roller, Pad or Airless Spray	Clean Water	Warm Soapy Water	60 Minutes	4 Hours	30 Days
<b>PRODUCT NAME:</b> 1000 Line HEAVY DUTY Latex / Flat		An eggshell latex enamel that dries to a durable, smooth finish. It exhibits excellent dirt and stain resistance and washes like an enamel without harm to the finish.						
<b>WHERE TO USE:</b>		Drywall Plaster Wood Metal	Its angular sheen makes it ideal for wood or walls throughout residential or commercial structures. It is designed to cover properly prepared surfaces in one coat..					
<b>Surface Preparation:</b>		<p>New Work: The surface to be coated must be clean and free of dust, grease, wax, rust, oil, and bleeding stains.</p> <p>Priming –</p> <ul style="list-style-type: none"> <li>Drywall – Self priming, but for best results use 1190 Latex Primer Sealer.</li> <li>Plaster – For best results use No. 50 BlockOut, 2000 Sungard.</li> <li>Wood – Alkyd Primer Undercoat, 37-11</li> <li>Ferrous Metal – Rust inhibiting metal primer such as 35-111, 2090 or 925-147.</li> <li>Galvanized – Acrylic Primer 36-11 or 180-11.</li> <li>Masonry – Use Primer Sealer 43-10 or 48-11. Block Filler 946-11.</li> </ul> <p>Repaint Work: On previously painted surfaces in good repair, no priming is generally necessary. On glossy surfaces remove the sheen with sandpaper or steel wool. Patch holes or cracks with appropriate filler. Spot prime bare areas with indicated primer. Remove any oil, chalk, dirt, wax or dust prior to recoating. Any loose or flaking paint should be removed and the edges feather sanded to product a smooth, uniform surface.</p>						
<b>Application:</b>		<p>Stir product thoroughly with a circular, lifting motion to disperse into a homogenous liquid.</p> <ul style="list-style-type: none"> <li>Roller – 3/8" to ¾ " nap, depending on surface texture.</li> <li>Brush – Nylon or polyester filament.</li> <li>Airless Spray – Tip size at atomization pressures will vary with type of equipment, and viscosity and temperature. An orifice of .017 - .019 will provide the most satisfactory spray pattern.</li> </ul> <p>Best results are more likely obtained by using quality application tools. Do not apply directly over chalky surfaces or bleeding stains. Apply only when surface and air temperatures are above 55° F.</p>						
<b>NOTE: Formulated without mercury or lead.</b>								

<b>Resin:</b>	Acrylic
<b>Solids:</b>	Weight – 54.9% Volume – 39.6%
<b>Weight Per Gallon:</b>	11.09 lbs.
<b>Viscosity:</b>	95 – 98 (Krebs Units)
<b>Specular Gloss:</b>	20 – 25% @ 85 degrees
<b>Recommended Film Thickness:</b>	Wet – 3.5 to 4.5 mils Dry – 1.4 to 1.8 mils
<b>VOC – VOS Statement:</b>	This product contains less than 3.17 lbs or 250 GPL per gallon.
<b>Cautions:</b>	<b>CAUTION!</b> Do not take internally. Close container after each use.  <b>KEEP OUT OF REACH OF CHILDREN.</b>

ADS -320

