



**Ceramic Satin  
Clear Wood  
Acrylic Sealer Interior  
100% Acrylic  
1590**

Type	Sheen	Spread Rate	Recommended Application	Thinner	Clean Up	DRY TIME		
						Tack Free	Re-coat	Cure
100% Acrylic	20-25 @ 60°	400-500 Sq Ft Per Gallon	Brush, Roller, or Spray	Clean Water	Warm Soapy Water	1 Hour	4 Hours	24 Hours
<b>PRODUCT NAME:</b> 1590 Ceramic Satin Clear Wood Acrylic Sealer Interior 100% Acrylic		This clear, water thinned sealer offers deep penetration into stucco, wood, concrete and masonry surfaces. It will form a tough film that repels water and helps reduce spalling and dusting. Will seal and refurbish a paint film that is showing signs of fading due to oxidation. Produces maximum intercoat adhesion between paint films. Forms a clear satin finish exhibiting outstanding hardness, durability, abrasion resistance and gloss retention.						
<b>WHERE TO USE:</b>		Wood Doors Trim	On interior areas such as trim, furniture, doors or cabinets. May also be used on semi-protected exterior surfaces such as entry doors.					
<b>SURFACE PREPARATION:</b>		Surface to be coated must be clean and free of dust, grease, dirt or wax. If wax is a suspect contaminate, remove with a commercial wax stripper. New interior wood must be sanded smooth. This product may not be used over sanding sealers containing silicone, wax or stearates. If a sanding sealer is desired, use 64-11 Acrylic Sanding Sealer or 67-11 Alkyd Sanding Sealer and allow 4 – 6 hours before sanding smooth. Very good results may also be achieved by using this waterborne clear as a sealer and topcoat allowing 2 to 4 hours dry time between coats and sanding lightly before applying.						
<b>APPLICATION:</b>		This varnish may be applied by brush, roller or spray. Stir thoroughly before and occasionally during application. Do not shake. Best rolling results are achieved with a ¼" short nap roller. For best brush application, use a good quality synthetic brush. When brushing or rolling, flow material on with a minimum of strokes. Thinning is not recommended, if necessary use water sparingly. Do not apply when surface or air temperatures are below 55° F. Sand lightly with fine sandpaper between coats. Apply Aqua-Plastic® in thin coats to avoid prolonged milky appearance of the film.						
<b>NOTE: Formulated without mercury or lead.</b>								

<b>RESIN TYPE:</b>	100% Acrylic
<b>SOLIDS:</b>	Weight – 43.4% Volume – 38.1%
<b>WEIGHT PER GALLON:</b>	9.1 lbs.
<b>SPECULAR GLOSS:</b>	20 - 25% @ 60 degrees
<b>RECOMMENDED FILM THICKNESS:</b>	Wet – 3.0 to 3.5 mils Dry – 0.8 to 1.0 mils
<b>VOC – VOS STATEMENT:</b>	This product contains less than 1.25 lbs or 150 GPL per gallon.
<b>CAUTIONS:</b>	<b>CAUTION!</b>  <b>Do not take internally. Close container after each use.</b>  <b>KEEP OUT OF REACH OF CHILDREN.</b>

Rev. 01/2013

