



**FILL AND FINISH  
VINYL / ACRYLIC  
LATEX SATIN BLOCK- FILLER  
539 - 11  
SECTION NO. 2 ADS 350**

Type	Sheen	Spread Rate	Recommended Application	Thinner	Clean Up	DRY TIME		
						Tack Free	Re-coat	Cure
Vinyl Acrylic Latex	Satin	Up to 75 Sq Ft Per Gallon	Brush, Roller, Or Airless Spray	Clean Water	Warm Soapy Water	30 Minutes	8 Hours	7 - 10 Days
<b>PRODUCT NAME:</b> 539-11 Hi-Hide Vinyl/Acrylic Latex Satin Block Filler		This Latex Satin Block Filler is formulated with high resin content, allowing it to fill concrete block in one brush, roller or spray / back-roll coat, when applied at the rate of 75 sq ft per gallon.						
<b>WHERE TO USE:</b>		Cement Concrete Masonry Blocks      On interior cementitious substrates where a smooth, uniform satin finish is desired.						
<b>Surface Preparation:</b>		Surface to be painted must be clean and free of dust, grease, wax, rust stains and form release agents. Remove the mildew by scrubbing with a strong solution of non-ammoniated cleanser (or T.S.P.) and warm water with 8 oz. of bleach per gallon. Rinse thoroughly and allow to dry. Dense smooth precast or poured in place concrete surfaces may require abrasion to create a profile for proper adhesion. Do not apply to uncured concrete surfaces; the pH of the substrate must be less than 9 or less. If the pH is higher than 9 prime the substrate with 5090 Pro Prime Barrier Coat.						
<b>Application:</b>		Stir product with a circular lifting motion. This block filler may be brushed, rolled or sprayed and back-rolled. Apply generously as it comes from the container. Care must be taken to assure that large voids are filled during spray application. Back rolling with a wet roller is recommended for a more uniform fill. An airless .025 - .030" fluid tip should be used for spray application. Do not apply when surface or air temperatures are below 50°F Latex Block Filler may be thinned sparingly with clean water to proper spray consistency. Thinning is not normally required for brush or roller application. A second coat may be applied if required.						
<b>NOTE: Formulated without mercury or lead.</b>								

<b>Resin Type:</b>	Vinyl Acrylic / Acrylic
<b>Solids:</b>	Weight – 55.0% Volume – 41.5%
<b>Weight Per Gallon:</b>	10.6 lbs.
<b>Viscosity:</b>	117-125 (Krebs Units)
<b>Flash Point:</b>	200° F or over (TT-P-141, Method 4293)
<b>Specular Gloss:</b>	20 –25% @ 60 Degrees
<b>Sag Rating:</b>	Pass 20 mils (Lenetta)
<b>Recommended Film Thickness:</b>	Wet – 16.0 – 20.0 Mils Dry – 8.4 – 10.5 Mils
<b>VOC – VOS Statement:</b>	This product contains 73 grams of VOCs per Liter.
<b>Cautions:</b>	<b>CAUTION:</b>  Do not take internally. Close container after each use. KEEP FROM FREEZING KEEP OUT OF REACH OF CHILDREN.