



PRO - TECH
Latex / Semi-Gloss
2607 Line
 SECTION NO. 2 ADS-307

Type	Sheen	Spread Rate	Recommended Application	Thinner	Clean Up	DRY TIME		
						Tack Free	Re-coat	Cure
100% Acrylic	Semi-Gloss	Up to 350 Sq Ft Per Gallon	Brush, Roller, Pad or Spray	Clean Water	Warm Soapy Water	60 Minutes	4 Hours	30 Days
PRODUCT NAME: 2607 Line Pro-Tech Latex / Semi-Gloss		This Latex/Semi-Gloss Enamel is suited for wall and trim applications in kitchens, bathrooms, family rooms, hallways and children's bedrooms where routine cleaning is needed. Fast dry, low odor and pleasant semi-gloss sheen makes it an ideal finish for residential or commercial jobs. Excellent adhesion to aged gloss alkyd and other difficult to adhere to surfaces. This product complies with LEED Green Building Rating System GS-11 for interior non-flat paints.						
WHERE TO USE:		Drywall On interior wall and trim areas where a very cleanable, semi-gloss sheen is Plaster desired. Wood Metal Masonry Stucco						
Surface Preparation:		Surface to be painted must be clean and free of dirt, chalk, wax, grease, rust or loose, flaking paint. Dirt and chalk should be removed by scrubbing with warm soapy water and thoroughly rinsed with clean water. Wax should be removed with a commercial wax stripper or by solvent cleaning. Grease should be cleaned by using Coronado Sur-Prep I. Rust must be removed by hand sanding or by conscientious power tool cleaning. Remove loose paint by scraping. Feather sand rough edges to insure a smooth finish coat. Glossy surfaces must be dulled by lightly sanding. Remove sanding dust before paint application. Any exposed substrate should be spot primed with the appropriate primer. Priming: (New or Bare Surfaces) Drywall – Self priming, but for best results use 50 Block It or 5790 Plaster – Always use No. 50 Block It Wood – Alkyd Primer Undercoat 37-11 Ferrous Metal – Rust inhibiting metal primer such as 35-111, 2090 or 925-147 Galvanized – 100-10, 180-11 or 36-11 Masonry – Use Primer Sealer 43-10 or 48-11. To fill porous block use 946-11 Latex Block Filler.						
Application:		Stir product with a circular, lifting motion before you begin to paint. This semi-gloss enamel may be applied by brush, roller, pad, or spray techniques, at a rate of application not to exceed 350 sq ft per gallon. Surface texture and porosity will effect actual yield. For best brush application results, use a quality synthetic bristle brush. For roller application, use a 3/8" nap cover for smooth surfaces, a 3/8" or 1/2" nap cover for semi-rough surfaces and a 3/4" nap cover for rough surfaces. Thinning is not normally necessary, if required use water sparingly. For spray application, the semi-gloss enamel may be thinned with clean water, up to 10% reduction if necessary. Apply when surface temperature is above 50°F.						
NOTE: Formulated without mercury or lead.								

Resin Type:	100% Acrylic
Solids:	Weight - 52.6% Volume - 38.9%
Weight Per Gallon:	10.68 lbs.
Viscosity:	94 – 98 (Krebs Units)
Specular Gloss:	30 – 40% @ 60 Degrees
Recommended Film Thickness:	Wet – 4.0 – 4.4 mils Dry – 1.4 – 1.5 mils
VOC / VOS Statement:	This product contains less than 0.83 lbs or 100 GPL per gallon.
CAUTIONS:	CAUTION ! Do not take internally. Close container after each use. KEEP OUT OF REACH OF CHILDREN.