



HEAVY DUTY LATEX / SATIN

3800 LINE

SECTION NO. 2 ADS 323

Type	Sheen	Spread Rate	Recommended Application	Thinner	Clean Up	DRY TIME		
						Tack Free	Re-coat	Cure
Latex	Eggshell	Up to 350 Sq Ft Per Gallon	Brush, Roller Pad or Spray	Clean Water	Warm Soapy Water	60 Minutes	4 Hours	10 - 14 Days
PRODUCT NAME: 3800 HEAVY DUTY Latex / Satin		A professional grade vinyl acrylic enamel that is ideal for use in apartments, rental properties, commercial sites, residential or wherever a satin finish is desirable.						
WHERE TO USE:		Drywall On interior areas such as living rooms, bedrooms, dining rooms and hallways Plaster where an economical satin finish is desired. Wood Metal Masonry						
Surface Preparation:		Surface to be painted must be clean and free of dirt, chalk, wax, grease, rust or loose, flaking paint. Dirt and chalk should be removed by scrubbing with warm soapy water and thoroughly rinsed with clean water. Wax should be removed with a commercial wax stripper or by solvent cleaning. Grease should be cleaned by using Coronado Sur-Prep 1. Rust must be removed by hand sanding or by conscientious power tool cleaning. Remove loose paint by scraping. Feather sand rough edges to insure a smooth finish coat. Glossy surfaces must be dulled by lightly sanding. Remove sanding dust before paint application. Any exposed substrate should be spot primed with the appropriate primer. Priming - (new or bare surfaces) Drywall – Self priming, but for best results use #4190 Latex Primer Sealer Plaster – For best results use No. 50 Block-Out, #2100 Sungard. Wood – Alkyd Primer Undercoat, #37-11 Ferrous Metal – Rust inhibiting metal primer such as #35-11, #2090 or #925-147 Non-Ferrous Metal – Perma Bond #100-10 Galvanized - #100-10 Masonry – Masonry Sealer #43-10, #48-11, Block Filler #946-11.						
Application:		Stir product with a circular, lifting motion before you begin to paint. Satin Vinyl Acrylic may be applied by brush, roller, pad, or spray techniques, at a rate of application not to exceed 350 sq ft per gallon. Surface texture and porosity will effect actual yield. For best brush application results, use a quality synthetic bristle brush. For roller application, use a 1/4" or 3/8" nap cover for smooth surfaces, a 1/2" nap cover for semi-rough surfaces and a 3/4" nap cover for rough surfaces. For spray application, Satin Vinyl Acrylic may be thinned with clean water, up to 10% reduction if necessary.						
NOTE: Formulated without mercury or lead.								

Resin:	Vinyl Acetate / Acrylic
Solids:	Weight – 40% Volume – 25.5%
Weight Per Gallon:	10.2 lbs.
Viscosity:	88-96 (Krebs Units)
Specular Gloss:	25 – 35% @ 60 degrees
Recommended Film Thickness:	Wet – 3.5 to 4.0 mils Dry - .90 to 1.0 mils
VOC – VOS Statement:	This product contains less than 3.17 lbs. or 250 GPL per gallon.
Cautions:	CAUTION! Do not take internally. Close container after each use. KEEP OUT OF REACH OF CHILDREN.