



**DURASCUFF HP
100% ACRYLIC
EGGSHELL**

2871 LINE

Type	Sheen	Spread Rate	Recommended Application	Thinner	Clean Up	DRY TIME		
						Tack Free	Re-coat	Cure
100% Acrylic	Eggshell	Up to 400 Sq Ft Per Gallon	Brush, Roller, or Spray	Clean Water	Warm Soapy Water	30 Minutes	4 Hours	7 - 10 Days
PRODUCT NAME: DuraScuffHP Eggshell 2871 Line		DuraScuffHP is a premium scuff resistant paint, engineered to withstand the toughest conditions. This coating features excellent scuff and stain resistance, recommended for interior walls and trim where a scuff resistant coating is preferred. DuraScuffHP eggshell offers a fast drying formula ideal for areas where a quick turnaround is needed. Its superior sag resistance ensures excellent coverage and a smooth finish. Ideal for use on plaster, drywall, wood, primed metal and concrete or cinder block surfaces.						
WHERE TO USE:		Metal Wood Masonry Drywall DuraScuffHP Eggshell is suitable for high traffic areas in commercial settings, such as apartments, office settings, schools, cafeterias, hospitals, and hotels. For use on walls, trim, doors and cabinets.						
Surface Preparation:		<p>New Work: The surface to be coated must be clean and free of oil, grease, rust and other contaminants that could interfere with adhesion.</p> <p>The surface to be coated must be clean and free of oil, grease and other contaminants that could interfere with adhesion. Bare concrete block should be filled with 529-11 Latex Block Filler, prime drywall with 4190 Pro Prime Drywall Primer, Prime bare ferrous metal with the appropriate Alkyd Metal Primer.</p> <p>Repaint: The surface to be painted must be clean and free of dirt, chalk, mildew, wax, grease, rust or loose flaking paint. Dirt and chalk should be removed by thorough power washing. Mildew should be washed with a bleach and water solution. Wax should be removed by solvent cleaning. Grease and oil should be cleaned. Rust must be removed by hand sanding vigorously or by conscientious power tool cleaning. Remove loose paint by scraping. Feather sand rough edges to insure a smooth finish coat. Glossy surfaces must be dulled by lightly sanding. Remove sanding dust before paint application. Any exposed substrate should be spot primed with the appropriate primer.</p>						
Application:		Stir paint thoroughly with a circular, listing motion to assure even pigment dispersion. Roller – Use a short nap enameling cover. Brush – Use a polyester or nylon filament brush. Spray – May be sprayed using conventional or airless equipment. Can be thinned with clean water, up to 20% for spraying. For best results, use quality applicator tools. Do not sacrifice good results by using inexpensive tools. Apply only when surface and air temperatures are between 50°F and 90°F.						
NOTE: Formulated without mercury or lead.								

Resin Type:	100% Acrylic
Solids:	Volume – 39.2%
Weight Per Gallon:	10.42 lbs.
Viscosity:	95 – 100 (Krebs Units)
Flash Point:	200°F or over (TT-P-141, Method 4293)
Specular Gloss:	10 – 15% @ 60°
Light Reflectance:	95% (White or lightest colors)
Recommended Film Thickness:	Wet – 3.0 to 4.0 mils Dry – 1.0 to 1.5 mils
VOC – VOS Statement:	This product contains 150 grams of VOC/VOS per liter of coating (1.25 lbs. per gallon)
Cautions:	CAUTION! Do not take internally. Close container after each use. KEEP OUT OF REACH OF CHILDREN.

11/2024

