



PRO PRIME
Wood Primer / Sealer
Exterior Latex 100% Acrylic
4790

SECTION NO. 10 ADS-1104

Type	Sheen	Spread Rate	Recommended Application	Thinner	Clean Up	DRY TIME		
						Tack Free	Re-coat	Cure
100% Acrylic	Flat	Up to 350-400 Sq Ft Per Gallon	Brush, Roller, Pad or Spray	Clean Water	Warm Soapy Water	1 Hour	2 Hours	7 Days
PRODUCT NAME: 4790 Pro Prime Wood Primer/Sealer 100% Acrylic		This professional grade Exterior 100% Acrylic Latex Primer was formulated for use on new non-bleeding wood, masonry, and no-ferrous metals. Resists cracking over bare exterior plywood, T-1-11, Douglas Fir, and Southern Yellow Pine. This non-flammable, blister resistant, fade resistant coating is easy to apply and water thinnable.						
WHERE TO USE:		Wood Masonry Brick Cement / Asbestos Hardboard On exterior siding, trim, fascia, fences and gutters. Will seal staining type woods, such as cedar and redwood in two coats.						
SURFACE PREPARATION:		Stir thoroughly before using. Surface must be clean and free of dirt, grease, grime and excessive chalk. Remove pitch and tar spots and seal knots. Remove all chalk, loose and flaking paint and dirt by scraping, power washing, wire brushing or sanding. Fill all holes and cracks and fill any voids or surface imperfections with appropriate filler. <u>NEW WORK:</u> A coat of #4790 Exterior Primer/Sealer or #560 O'Leary Exterior Oil Primer is recommended on new wood. On staining type woods such as redwood, cedar or mahogany, one or two coats of #2090 O'Leary Acrylic Bonding Primer will minimize or eliminate stain development. Masonry or brick surfaces if primer is needed #4790. Metal surfaces must be primed with #1220 O'Leary Universal Metal Primer. <u>OLDWORK:</u> Over old latex finish in good condition, apply one coat of Pro-Tech Latex House Paint. When changing from an oil paint system to a latex system, the surface should be primed with 4790 Exterior Primer/Sealer or #560 O'Leary Exterior Oil Primer. On glossy wood surfaces, sand thoroughly and apply 4790 Exterior Primer/Sealer or #560 O'Leary Exterior Oil Primer. For chalking masonry surfaces. Surface conditioner should be applied first. Bare metal surfaces (nail heads) must be primed with #1220 O'Leary Universal Metal Primer.						
APPLICATION:		Stir product with a circular, lifting motion before you begin to paint. Sungard Acrylic House Paint Primer may be applied by brush, spray, pad or roller at a rate of application not to exceed 350 sq ft per gallon. Surface texture and porosity will effect actual yield. For best brush application results, use a quality synthetic filament brush. For roller application, use a 3/8" or 1/2" nap cover for rough surfaces. For spray application, this product may be thinned with clean water, up to 10% reduction if necessary. Apply only when surface and air temperatures are between 35°F and 90°F.						
NOTE: Formulated without mercury or lead.								

Revised 04/2015

RESIN:	100% Acrylic
SOLIDS:	Weight – 42.8% Volume – 32.0%
WEIGHT PER GALLON:	10.12 lbs.
VISCOSITY:	92 – 96 (Krebs Units)
SPECULAR GLOSS:	4 – 10% @ 85 Degrees
RECOMMENDED FILM THICKNESS:	Wet – 3.5 to 4.0 mils Dry – 1.5 to 1.7 mils
VOC – VOS STATEMENT:	This product contains less than 1.0 lbs. or 120 GPL per gallon.
CAUTIONS:	CAUTIONS! Do not take internally. Close container after each use. KEEP OUT OF REACH OF CHILDREN! KEEP FROM FREEZING.

Revised 04/2015

ADS-1104

